

Hunter



Timberline 8x48





PRODUCT CERTIFICATE FINISHED PRODUCT LABORATORY

ASTM - ANSI A137.1

Mohawk Revestimentos Cocal do Sul Ltda . Rua Maximiliano Gaidzinski-sala 2, N. 245
88845-000 . Cocal do Sul- SC . Brasil . +55 (048) 3447-7777 . www.decortiles.com

Product:	HUNTER AC 19,7x120	Production Process:	Wet ceramic process
Code:	8056336	Work Size (W):	197,0 x 1200,0 mm 7,75 x 47,25 in
Class:	Bla	Nominal Size (N):	19,7X120 cm
Typology:	Porcelain tile	Thickness (Ew):	9,5 mm
Shade:	V3	Covering Area:	1,65m ² /box - 17,76sq.ft./box
Grout:	1 mm	Pieces per box:	7,00
Edge finish:	Rectified	Surface:	GL (Glazed)



	CHARACTERISTICS	TESTING METHOD	SPECIFICATION	RESULTS
USAGE RECOMMENDATION	FIR Indoor dry residential floors	Manufacturer's recommendation	According to the manufacturer's criteria	FLC WWS WFA
	FLC Indoor light commercial floors, including the areas FIR			
	FMC Indoor medium commercial floors, including the areas FLC and FIR			
	FHC Indoor heavy commercial floors, including the areas FMC, FLC, FIR			
	WID Indoor dry residential and commercial walls			
	FWI Indoor wet residential and commercial floors			
	WRC Indoor and outdoor, wet or dry, residential and commercial walls, including the areas WID. For regions reaching below freezing temperatures, non frost resistant tiles are indoor only.			
	WWS Swimming pool interior walls, including the areas WRC and WID			
	WFA External facades, including the areas WRC and WID			
	FHO Floor - Very Heavy Outdoor Commercial and Outdoor Residential			
	FMO Floor - Light to Heavy Outdoor Commercial and Outdoor Residential			
	FRH Floor - Ramp Very Heavy Outdoor Commercial and Outdoor Residential			
	FRM Floor - Ramp Light to Heavy Outdoor Commercial and Outdoor Residential			
PHYSICAL PROPERTIES	Water Absorption	ASTM C373-16	ANSI A 137.1: > 0,0 / ≤ 0,5	≤ 0,50
	Breaking Strength	ASTM C648-04	ANSI A 137.1: ≥275Lbf	≥275Lbf
	Frost Resistance	ASTM C1026-13	ANSI A 137.1: To declare	Yes
	Mohs hardness	C1895-20		N/A

	CHARACTERISTICS	TESTING METHOD	SPECIFICATION		RESULTS
CHEMICAL PROPERTIES	Stain Resistance	ASTM C1378-04	ANSI A 137.1:	To declare	Class A
	Chemical Resistance	ASTM C650-04	ANSI A 137.1:	To declare	Class B
DYNAMIC FRICTION COEFFICIENT - DCOF	Wet Dynamic Friction Coefficient - DCOF	ANSI A326.3-	ANSI A 137.1:	≥ 0,42	≥ 0,42

Note:

Verify if the product is adequate for the intended usage.

Sand may cause scratches in any type of covering (stone, wood, vinyl, or ceramic). For this reason, ceramic tiles are not warranted against scratches, especially concerning products with glossy surfaces. It is recommended special care during installation and use. In residential areas, we recommend protecting the base of furniture and appliances.

Negligence towards the intended use specified in this report, abnormal environmental action, climate factors, etc, is going to reduce the product's useful life, which may be shorter than the period declared by the manufacturer.

Tiles cleaning: Tiles with metallic and special glass finishes should be cleaned only with a cloth soaked in water and neutral detergent. Do not use acidic cleaning products or abrasive sponges that may damage the tile's surface.

On outdoor areas of regions where there is an incidence of snow, the frost resistance should always be analyzed. Only porcelain tiles are indicated for outdoors use in areas with a temperature equal to or less than 0°C / 32°F.

QR WARRANTY CODE:
Validate this certificate in:



COCAL DO SUL (SC), October 07th, 2025

Angela Waterkemper
CREA: SC-203551-9
Quality Assurance Manager